


EXPERT 85WMP – 85g/m² Matt white permanent “Marine Grade” sticker on paper release liner

Expert 85WMP is a 85g/m² matt aqueous coated polyester film, with a BS5609 compliant permanent pressure sensitive adhesive laminated to a 140gsm kraft paper release liner. The construction is optimised for dry toner print applications.



Physical characteristics

Property	Typical Value	Unit	Test Method
Total Thickness	225 +/- 7	μ	Electronic micrometer
Weight	245 +/- 6	g/m ²	Internal method
Face Film Thickness (no adhesive)	60 +/- 3	μ	Electronic micrometer
Liner Thickness	132 +/- 4	μ	Electronic micrometer
Gloss 60°	<4	%	BYK Gardner
Opacity	>96	%	TAPPI T519
Tensile Strength (Face)	MD 14 TD 15	KgF/mm ²	ASTM D882-83
Adhesive Peel on Stainless Steel	>12	N/25mm	FINAT 1 (30min dwell)
Adhesive Application Temperature	+5 to +50	°C	Internal Method

Compatibility

Suitable for most thermal transfer and dry toner (laser/LED/flash fusion) print processes, both mono and colour small-volume, mid-volume & production machines. On such machines the user must establish for themselves the optimum settings and paper path, being aware of the thickness and weight of the material. The printable surface is also suitable for screen print, offset litho (using only fully oxidising inks).

Applications and characteristics

- ✓Tear resistant, high stability, water resistant front face.
- ✓Ideal for signage and rugged labelling for harsh environments.
- ✓Matt surface promotes toner adhesion and smoothest imaging on a wide range of toner based printers.
- ✓BS5609 Marine immersion compliant adhesive with good instant tack & rapid adhesive build.
- ✓140gsm low-curl paper release.

Availability	Rolls
	130mm x 100m
Recommended conditions	
For use	10° C – 30° C, 40% - 55% RH
For storage	10° C – 20° C, 20% - 55% RH
Shelf life	18 months after delivery (under recommended storage conditions)

NOTICE: The information provided herein is correct to the best of our knowledge. No liability for any errors, facts or opinions is accepted. You must satisfy yourself as to the suitability of this product for your application. No responsibility for any loss as a result of any person placing reliance on any material contained herein can be accepted.