

## EXPERT 20BL – 200g/m<sup>2</sup> Backlight film

Expert 20BL is a 200gsm 2-side aqueous diffuse coated polyester film, optimised for dry toner print applications.



### Physical characteristics

Property	Typical Value	Unit	Test Method
Weight	199 +/- 5	gsm	Internal Method
Thickness	145 +/- 4	μ	Electronic Micrometer
Opacity	64 +/- 2	%	TAPPI T519
Gloss 60°	<4	%	BYK Gardner
Shrinkage	MD <1.0 TD <0.4	%	5 minutes @ 150° C (297mm length)
Tensile Strength	MD 17 TD 17	KgF/mm2	ASTM D882-83
Elongation at break	MD 115 TD 90	%	ASTM D882-83
Melting Point	250	° C	ASTM E794-85
Usage temperature	- 40 to 120	° C	Internal method

### Availability Sheets/Pack

A4	100
A3	100
SRA3	100

### Recommended conditions

For use	10° C – 30° C, 40% - 55% RH
For storage	10° C – 20° C, 20% - 55% RH
Shelf life	24 months after delivery (under recommended storage conditions)

### Compatibility

Suitable for most thermal transfer and dry toner (laser/LED/flash fusion) print processes, both mono and colour small-volume, mid-volume & production machines. On such machines the user must establish for themselves the optimum settings and paper path, being aware of the thickness and weight of the material. The printable surface is also suitable for screen print, offset litho (using only fully oxidising inks).

### Applications and characteristics

It has a smooth matt diffused surface giving a strong backlit image with excellent print adhesion and can be printed on both sides where equipment allows.

- ✓ Water resistant, wipeable and punchable.
- ✓ Ideal for presentations and backlit signs - no protection necessary!
- ✓ Also highly suitable for applications, such as, Frosted Binder Covers and Menu or Wine List inserts.

**NOTICE:** The information provided herein is correct to the best of our knowledge. No liability for any errors, facts or opinions is accepted. You must satisfy yourself as to the suitability of this product for your application. No responsibility for any loss as a result of any person placing reliance on any material contained herein can be accepted.