



master

Master 14WF

Glass-Clear Polyester Window Film



Thickness & Weight

142µm – 189 g/m²

Roll Widths & Lengths

762mm-30m
1372mm-30m
1542mm-30m

Recommended conditions

Printroom	15°C - 30°C, 30% - 65% RH
For use	-40°C - 80°C, 10% - 90% RH
For storage	10°C - 20°C, 20% - 50% RH
Shelf Life	24 months after delivery (under recommended storage conditions)

Compatibility

Mid Solvent



Eco Solvent



Latex



UV



Characteristics

- Glass-clear polyester film
- 100% water resistant
- High-gloss coating
- Antistatic back-coating avoids attracting dust and slipping in the printer

Applications

- Point of sales, displays
- Special window graphics
- Clear colour separation film
- Map overlays

Post Printing Information for Latex & Solvent Inks:

As with all filmic media, this product must be allowed to "Gas-out" after printing. This can be achieved by leaving the prints face up, ideally for 24 hours, to set and harden the unique scratch resistant properties. If unable to do this e.g. with a long print run, after printing the roll stand it vertically and loosely unwind as much as possible, to allow air in and gases out.

APPFACTORY - Inspired by print applications

+329 331 53 88

info@appfactorydigital.com

www.appfactorydigital.com